

Otoform[®] A softX



Technical Data Sheet

Intended use: Addition vulcanizing ear impression silicone

Manufacturer: Dreve Otoplastik GmbH
Max-Planck-Straße 31
59423 Unna / Germany

Composition:

Pos	chemical term
1	vinyle containing polydimethylsiloxane
2	silicic acid
3	filling materials
4	pigments
5	platin – catalyst

Color: pink

Processing time: 100 sec ± 15 sec at 23 °C

Setting time: 3 min ± 15 sec at 37 °C

Final hardness: 25 ± 2 Shore A

Consistency: medium bodied - Typ 2
(according to DIN EN ISO 4823)

Recovery from deformation: > 99.5 % (according to DIN EN ISO 4823)

Linear dimensional change: < 0.2 % (according to DIN EN ISO 4823)

Dreve Otoplastik GmbH

Max-Planck-Str. 31

59423 Unna / Germany

Tel.: 02303 / 8807-0

Fax: 02303 / 82909

otoplastik@dreve.de

www.dreve.com

These data result from measurements which are executed from time to time
in view of our quality management system.
This document is valid without any signature.

Rev. 3 / 10.2021
Page 1 of 1
TDS_Otoform A softX_GB